



## Technical Data Sheet

Effective Date: 12-Oct-2018

### **BRADY B-7541P SURFACE PRINTED POLYESTER OVER-LAMINATED WITH A CLEAR POLYESTER**

#### **Description:**

#### **GENERAL**

Brady B-7541P is a surface printed white polyester with a permanent acrylic pressure sensitive adhesive and over-laminated with a clear polyester film.

#### **SPECIAL FEATURES**

B-7541P is used for pipe markers and safety signs.

B-7541P gives excellent adhesion to low surface energy surfaces such as polypropylene and ABS, as well as on most powder coatings.

#### **REGULATORY/AGENCY APPROVALS**

**UL:** B-7541P is a UL Recognized Component to UL969 Labeling and Marketing Standard. See UL file MH12449 for specific details. UL information can be accessed online at *UL.com*. Search in *Certifications* area.

**BS 5609:** B-7541P black and red printing for GHS/CLP labeling has been tested by Smithers Pira and conforms to BS 5609:1986 Section 2 – 'Marine and Laboratory Performance of Label Base Materials' and to BS 5609: 1986 Section 3 – 'Laboratory Performance of Printed Labels'.

#### **ROHS Environmental Compliance**

Brady B-7541P is compliant to RoHS2 directive 2011/65/EU.

## Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.100 mm 0.020 mm 0.120 mm
Adhesion to:	ASTM D 1000	
-Stainless Steel	20 minute dwell 24 hour dwell	69 N/100 mm 77 N/100 mm
-Polypropylene	20 minute dwell 24 hour dwell	55 N/100 mm 62 N/100 mm
-Smooth ABS	20 minute dwell 24 hour dwell	74 N/100 mm 92 N/100 mm
-Textured ABS	20 minute dwell 24 hour dwell	14 N/100 mm 21 N/100 mm
-Powder Coated Metal	20 minute dwell 24 hour dwell	76 N/100 mm 81 N/100 mm
Drop Shear	PSTC-7	38 hours
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	225 g

Performance properties tested on digitally printed B-7541P material. Printed samples were laminated to aluminium and allowed to dwell 24 hours before exposure to the indicated environments.

PERFORMANCE PROPERTIES	TEST METHOD	TYPICAL RESULTS
High service temperature	Short term (1h) at 140°C	No visible effect
	Long term (30 days) at 120°C	No visible effect
Low service temperature	30 days at -40°C	No visible effect
Minimum application temperature		+2°C
Humidity resistance	30 days at 37°C and 95% R.H.	No visible effect

## Average Outdoor Durability:

Outdoor performance expectations for B-7541P are based on UV resistance testing in the Q-Sun Xenon Test Chamber

Model Xe-3 (Daylight Filter, Irradiance 0.35 W/m<sup>2</sup>, Wavelength 340nm, Continuous light at 63°C black panel temperature) and on weatherability testing in the QUV Accelerated Weathering Tester Model QUV/se, according to ASTM G154, Cycle 1. The test results suggest that B-7541P may be used successfully in outdoor environments for a period of up to 5 years. Actual outdoor life of product will depend on user definition of failure, climatic conditions, mounting techniques and material color. See note and warranty statement below for additional information.

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
Digitally printed samples are laminated to aluminium panels and allowed to dwell 24 hours prior to testing. Tests conducted at room temperature. Testing consisted of 5 cycles of 10 minute immersions in the specified test fluid, followed by 30 minute recovery periods. After final immersion, samples rubbed 10 times with cotton swab saturated with test fluid.	

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE	
	EFFECT TO LABEL STOCK EFFECT TO PRINT	EFFECT TO PRINT WITH RUB
Gasoline	nve	nve
Alcohol mixture	nve	nve
Toluene	nve	nve
Methyl Ethyl Ketone	nve	nve
Isopropyl Alcohol	nve	nve
Acetone	nve	nve
Diesel	nve	nve
n-Hexane	nve	nve
Iso-octane	nve	nve
Sulfuric acid solution (10%)	nve	nve
Sodium Chloride (10%)	nve	nve
Water distilled	nve	nve

\*Alcohol mixture is a mixture of 50% ethanol, 30% methanol and 20% distilled water Nve = No visible effect

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

**Trademarks:**

Polyken™ is a trademark of Testing Machines Inc.

ASTM: American Society for testing and Materials (U.S.A.)

PSTC: Pressure Sensitive Tape Council (U.S.A.)

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

## **WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2018 Brady Worldwide, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.